



PRODUCT SPECIFICATION AND PHYSICAL PROPERTIES ON CLAY BRICK

Product	Class	Average Weight (kg)	Dimensions	Stated Work Size (mm)	Average CCS (MPa)	Certification
Autumn Travertine	FBA	2.6	Length	221	30.3	SABS Approved
			Width	101		
			Height	71		
Caramel Mix Travertine	FBA	2.6	Length	220	33.7	SABS Approved
			Width	99		
			Height	71		
Dapple Multi-Mix Dark Travertine	FBS	2.52	Length	219	33.9	SABS Approved
			Width	99		
			Height	70		
Dapple Multi-Mix Light Travertine	FBS	2.6	Length	221	31.4	SABS Approved
			Width	100		
			Height	70		
Dapple Travertine	FBS	2.6	Length	221	33.7	SABS Approved
			Width	99		
			Height	70		
Fire Box Travertine	FBA	2.6	Length	220	32.5	Non SABS
			Width	99		
			Height	70		
Golden Travertine	FBS	2.6	Length	219	41.8	SABS Approved
			Width	99		
			Height	70		
Honey Glow Mix Travertine	FBA	2.51	Length	220	29.7	SABS Approved
			Width	99		
			Height	70		
Ivory Travertine	FBS	2.57	Length	219	38.2	SABS Approved
			Width	99		
			Height	70		
Golden Onyx Travertine	FBA	2.48	Length	217	41.3	Non SABS
			Width	97		
			Height	70		
Clay Plaster Travertine (Mix)	NFP	2.6	Length	226	17.3	Non SABS
			Width	101		
			Height	72		



PRODUCT SPECIFICATION AND PHYSICAL PROPERTIES ON ROOF TILE

Product	Dimensions	Stated Work Size (mm)	Hanging Length (mm)	Cover Width (mm)	Average Weight (Kg)	Average Strength N/mm	Certification
Double Roman Classic	Length	420	400	300	4.1	5.0	SABS Approved
	Width	330					
Double Roman X-treme	Length	420	400	300	4.6	5.0	SABS Approved
	Width	330					
Double Roman Tuscan	Length	420	400	304	5	5.0	SABS Approved
	Width	333					